


# YAC-O187



## 3-Glycidoxypropyltrimethoxysilane

**CAS No. 2530-83-8**

### Specifications:

Tests	Specification
Appearance	Colorless transparent liquid
Assay	≥98.0%
Refractive index n <sup>25</sup> D	1.4220-1.4320
Chlorine	≤20 ppm
Water dissolution time	≤20 min
Hazen (Pt-Co)	≤30

**Package:** 200Kg Drum.

### Application:

- Finish or a size ingredient for glass fiber / glass fabric composites.
- Additive to polyurethane resins for foundry resins.
- Primer or additive for sealants and adhesives.
- For pretreatment of fillers and pigments or as an additive to the polymer of mineral filled composites.

**Storage:** Non dangerous cargo. Keep away from open flames, hot surfaces and sources of ignition. Keep container tightly closed.



**Recommend Shelf Life:** 12 months.