


YAC-V171

Vinyltrimethoxysilane

CAS No. 2768-02-7



Specifications:

Tests	Specification
Appearance	Colorless transparent liquid
Assay	≥99.0%
Color (Pt-Co)	≤30
Density (20°C)	0.9668~0.9768g/cm ³
Refractive Index (n _D ²⁵)	1.3880~1.3980

Package: 190Kg/Drum or 950Kg/IBC

Application:

- It is suitable for wet curing polymer materials such as polyethylene. The characteristic of this process is that vinyl silane is grafted with polymer materials through peroxides during extrusion.
- It can react with inorganic fillers and organic polymers, so it can be used as an effective bonding accelerator, but also as a dehumidifier and so on.

Storage: Keep away from open flames, hot surfaces and sources of ignition. Keep container tightly closed.



Recommend Shelf Life: 12 months.